



# WearSpray 500™

Chemically Bonded Quartz-Ceramic



## Features & Benefits

Wear-Con Densit® WearSpray 500™ Chemically Bonded Quartz-Ceramic wear resistant lining is a sprayable, trowellable one-component ready-mix wear compound, allowing for fast monolithic coverage over large surface areas and system components with complex geometric shapes. Along with the flexibility of multi-dimensional coverage with seamless thickness graduation, WearSpray 500™ is fast and easy to install and can be used after just 24 hours.

## Installation

Wear-Con Densit® WearSpray 500™ can be installed in five simple steps:

1. Install mesh. WearSpray 500™ should be installed on a standard expanded metal mesh welded on the steel casing.
2. Mix dry WearSpray 500™ compound for 1 minute with a paddle mixer. Product must be kept completely dry until used.
3. Add water and fibers, then mix for 8 minutes with a paddle mixer. A significant change in consistency of the material (from a dry powder to wet mortar) must be observed within 3 minutes from addition of water.
4. Convey mixed WearSpray 500™ through recommended pump, then spray onto mesh. Smooth surface if needed. Avoid making contact with aluminum or galvanized steel when using WearSpray 500™.
5. Apply Densit® Curing Compound.

For more details refer to the “Densit® WearSpray™ Video”.

## Technical Specifications

Wear-Con Densit® WearSpray 500™ is a high-strength wear compound combined with quartz aggregates to provide excellent protection against moderate wear at temperatures up to 750°F (see reverse for more technical data).

## Sizes

Wear-Con Densit® WearSpray 500™ is delivered in 55 lb bags.

*(See reverse for more technical data.)*

2845 E. Heartland Drive  
Liberty, MO 64068

**888-4WEARCON (888-493-2726)**  
**816-587-1923 • Fax 816-587-2055**  
[info@wearcon.com](mailto:info@wearcon.com)  
[www.wearcon.com](http://www.wearcon.com)



# WearSpray 500™

Chemically Bonded Quartz-Ceramic

Technical Data			
Properties		Standard	Densit® WearSpray 500™
Density	kg/m <sup>3</sup> (lb/ft <sup>3</sup> )	EN 1015-6	2270 (142)
Compressive Strength	MPa	EN 12190	100
Flexural Strength	MPa	EN 196-1	15
Dynamic E-modul	MPa	EN	70 - 75 10 <sup>3</sup>
Casting Shrinkage	vol. %	-	0.2
Thermal Conductivity	w/m°C	-	1.5
Coeff. of Thermal Expansion	1/°C (1/°F)	EN 1770	10x10 <sup>-6</sup> (5.6x10 <sup>-6</sup> )
Heat Capacity	KJ/kg°C	-	0.9 - 1.0
Max. Service Temp.	°C (°F)	-	400 (750)
Abrasion Resistance	cm <sup>3</sup> /50cm <sup>2</sup>	DIN 52108	2.5 - 3.5
Erosive Resistance	min/cm <sup>3</sup>	-	55
Chemical Composition	CaO	EN 196-10	15%
	SiO <sub>2</sub>		82%
	Al <sub>2</sub> O <sub>3</sub> + TiO <sub>2</sub>		1%
	Fe <sub>2</sub> O <sub>3</sub>		<0.2%
	Cr <sup>6+</sup>		<0.0002%
Bag Size	kg (lb)	-	25 (55)
Pallet Size	kg (lb)	-	1250 (2755)

Consumption	
at 25 mm	
Densit® WearSpray 500™	54 kg/m <sup>2</sup>
Densit® WearSpray™ Fibers	54 g/m <sup>2</sup>
Densit® Anchoring Mesh	1 m <sup>2</sup> /m <sup>2</sup>
Densit® Curing Compound	0.25 l/m <sup>2</sup>

Consumption	
at 40 mm	
Densit® WearSpray 500™	87 kg/m <sup>2</sup>
Densit® WearSpray™ Fibers	87 g/m <sup>2</sup>
Densit® Anchoring Mesh	1 m <sup>2</sup> /m <sup>2</sup>
Densit® Curing Compound	0.25 l/m <sup>2</sup>

The figures contained herein are typical values. The dry mortar is quality inspected in accordance with the Densit® ISO 9001:2000 certified by Lloyd's Register Quality Assurance.

Please contact Wear-Concepts, Inc. for more information.

(See reverse for more information.)



**888-4WEARCON (888-493-2726)**  
**816-587-1923 • Fax 816-587-2055**  
[info@wearcon.com](mailto:info@wearcon.com)  
[www.wearcon.com](http://www.wearcon.com)

2845 E. Heartland Drive  
 Liberty, MO 64068

DENS-C-WS

11-17

**Densit**