



**Densit**

# WearFlex 500™

Chemically Bonded Quartz-Ceramic



## Features & Benefits

Wear-Con Densit® WearFlex 500™ Chemically Bonded Quartz-Ceramic wear resistant lining is a trowellable, one-component ready-mix wear compound combined with wear-resistant aggregates to provide a tough and long-lasting wear solution. WearFlex 500™ is applied directly to an anchoring mesh in thicknesses from 3/4" to 2", providing seamless graduation in lining thicknesses on almost any shape without vulnerable joints. Fast and easy to install, even overhead, WearFlex 500™ can be used after just 24 hours.

## Installation

Wear-Con Densit® WearFlex 500™ can be installed in five simple steps:

1. Install mesh. WearFlex 500™ should be installed on a standard expanded metal mesh welded on the steel casing.
2. Mix dry WearFlex 500™ compound for 1 minute with a paddle mixer. Product must be kept completely dry until used.
3. Add water and mix for 8 minutes with a paddle mixer. A significant change in consistency of the material (from a dry powder to wet mortar) must be observed within 3 minutes from addition of water.
4. Trowel WearFlex 500™ onto mesh. Avoid making contact with aluminum or galvanized steel when using WearFlex 500™.
5. Apply Densit® Curing Compound.

For more details refer to the "Densit® WearFlex™ Manual".

## Technical Specifications

Wear-Con Densit® WearFlex 500™ is a high-strength wear compound combined with quartz aggregates to provide excellent protection against moderate wear at temperatures up to 750°F (see reverse for more technical data).

## Sizes

Wear-Con Densit® WearFlex 500™ is delivered in 55 lb bags.

*(See reverse for more technical data.)*

2845 E. Heartland Drive  
Liberty, MO 64068

**888-4WEARCON (888-493-2726)**  
**816-587-1923 • Fax 816-587-2055**  
**info@wearcon.com**  
**www.wearcon.com**



# WearFlex 500™

Chemically Bonded Quartz-Ceramic

Technical Data			
Properties		Standard	Densit® WearFlex 500™
Density	kg/m <sup>3</sup> (lb/ft <sup>3</sup> )	EN 1015-6	2400 (150)
Compressive Strength	MPa	EN 12190	100
Flexural Strength	MPa	EN 196-1	16
Dynamic E-modul	MPa	EN	70 - 80 10 <sup>3</sup>
Casting Shrinkage	vol. %	-	0.2
Thermal Conductivity	w/m°C	-	1.5
Coeff. of Thermal Expansion	1/°C (1/°F)	EN 1770	10x10 <sup>-6</sup> (5.6x10 <sup>-6</sup> )
Heat Capacity	KJ/kg°C	-	0.9 - 1.0
Max. Service Temp.	°C (°F)	-	400 (750)
Abrasion Resistance	cm <sup>3</sup> /50cm <sup>2</sup>	DIN 52108	2.5 - 3.5
Erosive Resistance	min/cm <sup>3</sup>	-	55
Chemical Composition	CaO	EN 196-10	18%
	SiO <sub>2</sub>		80%
	Al <sub>2</sub> O <sub>3</sub> + TiO <sub>2</sub>		1%
	Fe <sub>2</sub> O <sub>3</sub>		<0.2%
	Cr <sup>6+</sup>		<0.0002%
Bag Size	kg (lb)	-	25 (55)
Pallet Size	kg (lb)	-	1250 (2755)

Consumption	
at 25 mm	
Densit® WearFlex 500™	59 kg/m <sup>2</sup>
Densit® Anchoring Mesh	1 m <sup>2</sup> /m <sup>2</sup>
Densit® Curing Compound	0.25 l/m <sup>2</sup>

Consumption	
at 40 mm	
Densit® WearFlex 500™	94 kg/m <sup>2</sup>
Densit® Anchoring Mesh	1 m <sup>2</sup> /m <sup>2</sup>
Densit® Curing Compound	0.25 l/m <sup>2</sup>

The figures contained herein are typical values. The dry mortar is quality inspected in accordance with the Densit® ISO 9001:2000 certified by Lloyd's Register Quality Assurance.

Please contact Wear-Concepts, Inc. for more information.

(See reverse for more information.)



**888-4WEARCON (888-493-2726)**  
**816-587-1923 • Fax 816-587-2055**  
[info@wearcon.com](mailto:info@wearcon.com)  
[www.wearcon.com](http://www.wearcon.com)

2845 E. Heartland Drive  
 Liberty, MO 64068

DENS-C-wf

12-18

**TW**  
**Densit**